

PRODUCT

**20% GR**  
(80% Virgin ptfе+ 20% graphite)

Property	Method	Units	Specification
Specific gravity	ASTM D792	g/cm <sup>3</sup>	2,120 – 2,180
Tensile strength	ASTM D4894	MPa	≥ 14
Elongation	ASTM D4894	%	≥ 140
Hardness	ASTM D2240	Shore D	≥ 55
Deformation under load (140 Kg/cm <sup>2</sup> for 24 hrs. At 23°C)	ASTM D621	%	9,5 - 11
Permanent deformation (after 24 hrs. Relaxation at 23°C)	ASTM D621	%	4,5 – 5
Coefficient of linear thermal expansion (T= 25 - 100 °C)		10 <sup>-5</sup> /°C	7 – 12
Coefficient of static friction			0,12 – 0,14
Coefficient of dynamic friction			0,09 – 0,11
Volume resistivity	ASTM D257	Ohm cm	10 <sup>5</sup>
Ageing and weatherability			Stable over 20 years of exposure
Service Temperature		C°	-200/ +260

Properties:

- Good thermal conductivity, low coefficient of friction, low permeability.

Main applications:

- In dynamic seal applications and where self-lubricating properties are important (eg. steering or shock absorber gaskets for light and heavy duty vehicles).

Date: 12/2009